


CARPENTER LTD BLOCK PLANT	INDIVIDUAL SPECIFICATION SHEET GLOSSOP PLANT	
GRADE/REF : RP18125		
<u>CHARACTERISTIC</u>	<u>SPECIFICATION</u>	<u>TEST METHOD</u>
APPARENT PIECE DENSITY	17.1–18.9 Kg/m ³	BS EN ISO 845 : 2009 (ISO 845 : 2006)
NOMINAL HARDNESS	105–145 Newtons	BS EN ISO 2439:METHOD B 2001
TENSILE STRENGTH	70 kPa (Min)	BS EN ISO 1798: 2008
ELONGATION @ BREAK	150 % (Min)	BS EN ISO 1798: 2008
COMPRESSION SET (DRY)	10 % (Max)	BS EN ISO 1856: 2001
FORM ISSUE No. 5	RAISED: 11/04/11	ISSUED BY: L McQuillan

*NOTE: THE CLASSIFICATION CLAIMED IS BASED ON IN HOUSE TEST RESULTS

EG_400/04/300709