


# Plastazote® LD33

## Low Density Polyethylene Foam

### Property Data Sheet



Plastazote® is a closed cell, cross-linked polyethylene foam manufactured using a unique production process. This data sheet characterises Plastazote foam LD33 which is available in sheet form and is fabricated by modern techniques and can be thermoformed into shapes.

Property	Test Procedure	Units	LD33
<b>Nominal Density - Skin/Skin</b>	BS ISO 7214 1998	kg/m <sup>3</sup>	33
<b>Cell Size – Typical Diameter</b>	Internal	mm	0.37
<b>Compression Stress-Strain</b>	BS ISO 7214 1998		
10% compression		kPa	51
25% compression		kPa	69
40% compression		kPa	102
50% compression		kPa	137
<b>Compression Set</b>	BS ISO 7214 1998		
25% comp., 22hr, 23°C	25 mm cell-cell		
½ hr recovery		% set	10
24hr recovery		% set	3
50% comp., 22hr, 23°C			
½ hr recovery		% set	22.5
24hr recovery		% set	13.5
<b>Tensile Strength</b>	ISO 7214 1998	kPa	440
<b>Tensile Elongation</b>		%	155
<b>Tear Strength</b>	BS EN ISO 8067 1995	N/m	785
<b>Shore Hardness OO Scale</b>	ISO 868 1985		
10mm cell/cell thickness		OO	58
<b>Recommended operating temperature range*</b>	Internal	°C	+100 max -70 min
<b>Thermal Conductivity</b>	ISO 8302 1991	W /m.K	0.0405
mean temp of 10°C			
<b>Flammability</b>			
<b>Automotive</b>	FMVSS.302 – Burn rate	<100mm/min.	Pass: 7 mm and thicker
<b>Horizontal Burn Rate</b>	ISO 7214 1998		
5mm thick		mm/sec	1.6
13mm thick		mm/sec	1.0

**\* RECOMMENDED OPERATING TEMPERATURE RANGE**

The maximum operating temperature shown is defined as the temperature which will typically cause a linear shrinkage of 5% after a 24hr exposure period, using sample dimensions of 100mm x 100mm x 25mm. This figure is provided for general guidance only. The actual level of shrinkage the foam will undergo at any particular temperature is dependant on a number of system variables such as, sample dimensions, cell size, loading conditions and exposure period.

**EXCLUSION OF LIABILITY**

This is a general guide only and Polyformes Ltd assumes no obligation or liability for the information in this document. No express or implied warranties are made and Customers are responsible for determining whether products and the information given are appropriate for the Customer's intended use.

For any further detailed information or specific material data, please contact our Technical Department on +44 (0)1525 852 444 or e-mail [info@polyformes.co.uk](mailto:info@polyformes.co.uk)